



230G

Nylon 6, 30% Glass Fibre Reinforced Compound.

Beetle 230G offers excellent mechanical performance coupled with good surface finish.

General Properties

Polymer Type	PA6
Filler / Reinforcement	Glass Fibre Reinforced
Processing Method	Injection Moulding
Form	Uniform Granules

Physical Properties	Test Method	Unit	D-A-M
Density	ISO 1183	g/cm ³	1.37
Water absorption (humidity)	ISO 62	%	2

Mechanical Properties	Test Method	Unit	D-A-M	Conditioned
Tensile Modulus	ISO 527-2	MPa	8500	
Tensile Stress @ Break	ISO 527-2	MPa	175	105
Tensile Strain @ Break	ISO 527-2	%	4	7
Flexural Modulus	ISO 178	MPa	8000	4000
Flexural Strength	ISO 178	MPa	230	110
Charpy Notched Impact	ISO 179/1-eA	kJ/m ²	13	35
Charpy Unnotched Impact	ISO 179/1-eU	kJ/m ²	55	

Thermal Properties	Test Method	Unit	D-A-M
Heat Distortion Temperature @ 0.45MPa	ISO75-2	°C	> 200
Heat Distortion Temperature @ 1.8MPa	ISO75-2	°C	> 175

Flammability Properties	Test Method	Unit	D-A-M
Flame Rating	Internal test (UL94)	*	HB (1.5mm)

Electrical Properties	Test Method	Unit	D-A-M	Conditioned
Surface Resistivity	IEC 60093	ohms	1.00E+15	1.00E+13
Volume Resistivity	IEC 60093	ohms.cm	1.00E+15	1.00E+12
Electric Strength (3mm)	IEC 60243-1	kV/mm	11	8
Comparative Tracking Index	IEC 60112	V	525	

Recommended Processing	Unit
Drying Temperature	°C
Drying Time	Hours
Processing Temperatures (Barrel)	°C
Melt temperature range	°C
Mould Temperature	°C

The material is supplied predried. Additional drying will be necessary if the material is open to the air for more than 2 to 3 hours. Redrying is also recommended after prolonged storage in undisturbed original packaging. The appearance of splash marks on the surface of mouldings indicates excessive moisture is present. Excessive drying temperature or duration will lead to progressive yellowing of natural or light colours.

Packaging and Storage

25Kg Moisture proof Aluminium sacks (Standard packaging). May be supplied in Octabins, Big bags, Bulk Silo etc, on request.
Store in dry, well ventilated areas away from heat sources.

The information given in this document is accurate to our knowledge on date of publication.
All data provided is based on typically achieved values and not to be taken as specifications.
Values will differ with addition of additives, pigments or other materials. Polyram UK Ltd gives no guaranty or warranty in connection with this data and it is to be used at individuals own discretion and risk.



Date of Issue - June 2020

Polyram UK Limited, Ward Industrial Estate, Church Road, Lydney, Glos, GL15 5EL
Tel: +44 (0)1594 842 406 email: enquiries@polyram-group.com www.polyram-group.com
VAT Registered No. GB844157718 Registered in England No. 05177839