

Property	Unit	Test Method	Specification Range
Melt Flow Rate (190 °C – 2.16 kg)	g/10min	ISO 1133-1	0.28 – 0.32
Density	g/cm ³	ISO 1183-2 & ISO 1183-1	0.957 – 0.959

Date of issue: 27.02.2020

European Sales Office

Sibur International GmbH

Prinz Eugen Straße 8-10

1040, Vienna, Austria

Tel.: +43 1 370 8000

E-mail: polyolefins@sibur-int.com